



## GENERAL DESCRIPTION

- Presstick 346UV is a special adhesive based on PU dispersion.
- Excellent for the adhesion of PVC, PP, PET, ABS foils onto MDF using membrane/vacuum press application.
- Presstick 346UV has a very high initial tack. High heat resistance.
- Can be used as 2K with the addition of 3-7% Isocyanat hardener (Presstick Hardener 100).
- UV indicator is incorporated.

## APPLICATION

- The adhesive should be sprayed , by a spraying gun with a nozzle diameter of 1 – 2 mm.
- It is recommended to apply 2 layers on the Edges.
- Adhesive must be fully dried after spraying and before activation.
- Adhesive should be filtered and mixed properly before use.

## TECHNICAL DETAILS

Solid Content	42 ± 1%
Viscosity at 23°C (Brookfield RVT 20 rpm/spindle 2)	1,500 cps (±200)
Density (g/cm <sup>3</sup> )	1.05 (± 0.01)
pH	Approx. 7
Coverage	60-120 gr/m <sup>2</sup>
Form	white liquid
Min. Film Forming Temperature	7°C
Min. Activation Temperature	60°C
Storage Stability	8 months from shipment day if stored at 23°C in the original sealed containers. Temperature above 30°C must be avoided. The product is sensitive to frost and should not be kept at temperatures lower than 5°C.
Packing*	18/20k <sup>g</sup> buckets, 20/22 k <sup>g</sup> jerrycans, 1,100 k <sup>g</sup> IBC.

This information presented here is based on the best data available and is believed to be correct. However nothing stated in this bulletin is to be taken as a warranty, expressed or implied regarding the accuracy of the information or the use of the product.

WWW.PRESSTICKADHESIVE.COM

**PRESSTICK**  
ADVANCED PU DISPERSION FORMULA

BY

**Polystick**  
Quality you can stick to

POLYSTICK LTD. / 12 A EHUD KINAMON ST.  
BAT YAM 5959220 ISRAEL / TEL. 972-3-5515560  
FAX. 972-3-5515564 / OFFICE@POLYSTICK.COM

